TempRite® 88031 CPVC Industrial Grade Molding Compound



	UNITS	VALUE	Standard
	ONTO	VALUE	Otaridard
Deflection Temperature Under Load (264 psi, annealed)	°F	212	ASTM D648
Impact, Izod, notched	ftlbs/in	1.6	ASTM D256
Tensile Strength at Yield	psi	8,400	ASTM D638
Tensile Modulus	psi	418,000	ASTM D638
Flexural Strength	psi	13,600	ASTM D790
Flexural Modulus	psi	419,000	ASTM D790
Coefficient of Linear Expansion	in/in°F	3.4x10 ⁻⁵	ASTM D696
Rockwell Hardness	R scale	119	ASTM D785
Specific Gravity		1.50	ASTM D792
Melt Flow Index (215°C, 21.6 kg)	g/10 min	9.2	ASTM D1238
Cell Classification		23447	ASTM D1784
Flammability 1.5 mm 2.3 mm 3.0 mm		V0, 5VB V0, 5VA V0, 5VA	UL 94
NSF Status		Approved	NSF 14, 61

88031vii

This document does not represent a product specification. The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

Lubrizol Advanced Materials, Inc. 9911 Brecksville Road Cleveland, OH 44141-3247 800-380-5397 www.tempritecpvc.com